Product Datasheet

d² Dura Grating 53mm Solid Top



Product Description


d² Dura Grating is a new patent pending GRP grating series that takes structural flooring to the next level. Available exclusively from Dura Composites, our Solid Top grating range achieves an industry-leading Class B fire rating according to BS EN 13501-1.

Designed, developed and manufactured by Dura Composites, d² Dura Grating's anti-slip surface is tested to over 1 million footfalls. It offers outstanding safety, performance and durability and is more cost-effective than traditional GRP grating in almost every scenario.

Product Details

Length (mm)	Width (mm)	Colours / Product Codes	Panel Weight (kg)	Weight (kg/sqm)	Open Mesh Size (mm)
3052	1057	Dark Grey (DG05303)	73.87	22.9	None
3682	1267	Dark Grey (DG05302)	106.83		





Product Applications

Common applications for d^2 Dura Grating include walkways, gantries, gully covers, service risers, access platforms, stair treads, ramps, bund flooring, roof walkways, fencing, gates, trash screens, pontoons, mezzanines and low-rise balcony flooring.

Packaging

Please see below for relevant packaging information for d² Dura Grating 53mm Solid Top.

Packaging	Product Information		
Maximum Products Per Pallet	20		
Dellat Directorione (rene)	3070 x 1060 x 1240		
Pallet Dimensions (mm)	3690 x 1240 x 1240		
Dellat Maialat (La)	1448		
Pallet Weight (kg)	2066		

Unlocking the Power of Composites[™] >>

Colours

Please see below for our d² Dura Grating RAL colours.

Dura Colours	RAL Number	
Dark Grey	7043	

Material

Glass Reinforced Polymer (GRP) d^2 Dura Grating is produced from glassfibres laminated together using an Orthophthalic Polyester Resin system and a gritted finish. It is resistant against a wide range of chemicals and temperature spectrums. Material samples are available on request, along with a copy of our chemical resistance data. Other resin types are available by special order.

Test Performance Overview

4S SI	ider Pendulum Test	BS EN 13501-1	BS 4592	European 20mm Ball Fall Test
72	PTV: 2 (dry)*, 62 (wet)*	Class B	Compliant	Compliant

^{*}Maintains 95% of slip resistance after 1.1 million footfalls.

For more information please refer the Technical Installation Manual or speak to your Dura Composites Representative.

Load and Deflection Data

Deflection is shown in millimetres (mm), with all columns denoting clear spans. Green/red cell colours indicate above and below L/100, which is the equivalent of 1% deflection. To view data for alternative standard load deflection such as L/200, or specific data for your project, visit www.duracomposites.com/power-of-composites.

Point Load (PL)

	1300mm	1350mm	1400mm	1450mm	1500mm	1550mm
5.0 kN/ PL	8.2	8.9	9.6	10.4	11.2	12.0
5.5 kN/ PL	9.2	10.0	10.8	11.6	12.5	13.5
6.0 kN/ PL	10.3	11.1	12.0	13.0	14.0	15.0
6.5 kN/ PL	11.4	12.3	13.3	14.4	15.4	16.6
7.0 kN/ PL	12.5	13.6	14.7	15.8	16.9	18.2
7.5 kN/ PL	13.7	14.8	16.0	17.2	18.5	19.8

Maximum Spans (mm)

		-
Load	L/100	L/200
5.0 kN	1880	1020
5.5 kN	1740	900
6.0 kN	1600	800
6.5 kN	1460	720
7.0 kN	1340	660
7.5 kN	1240	620

Uniformly Distributed Loads (UDL)

	1600mm	1650mm	1700mm	1750mm	1800mm	1850mm
2.5 kN/m ² UDL	7.6	8.4	9.4	10.3	11.4	12.6
3.0 kN/m ² UDL	9.0	10.0	11.1	12.3	13.6	14.9
3.5 kN/m ² UDL	10.4	11.6	12.8	14.2	15.7	17.2
4.0 kN/m ² UDL	11.8	13.1	14.5	16.1	17.7	19.5
4.5 kN/m ² UDL	13.2	14.7	16.4	18.1	20.1	22.1
5.0 kN/m ² UDL	15.0	16.7	18.5	20.5	22.6	24.8

Maximum Spans (mm)

Load	L/100	L/200
2.5 kN/m ²	2150	1630
3.0 kN/m ²	2010	1520
3.5 kN/m ²	1900	1440
4.0 kN/m ²	1810	1370
4.5 kN/m ²	1720	1300
5.0 kN/m ²	1640	1240

Key:







Safety Information

It is advisable to undertake a risk assessment, with particular focus on manual handling procedures. Wear appropriate gloves and coveralls to shield skin from abrasions. If shaping the product, it is essential to factor in the potential production of dust. To mitigate this, it is vital to either suppress the dust at source or employ effective extraction methods. We strongly recommend the use of appropriate respiratory protective equipment (RPE), specifically filtering facepiece class 3 (FFP3) masks, alongside adequate eye protection to guard against dust.

Recyclability

Return to manufacturer or downcycle.

Sustainability

The embodied carbon for A1-A3 (production stage) as defined in BS EN 15804 is 3.8kg CO₂ eq/unit.

Common Fixing Options

Some of the most common stainless steel fixing options are shown below. For a full list of fixings please see the d² Dura Grating brochure.



(BFX01003)





Extra Large Dome Washer (BFX02165)



Uni-Strut Clamps (DP05053)

Warranty

25 year limited warranty available. Please register your product with us within 30 days of your invoice date. Visit www.duracomposites.com/warranty.